



**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar  
İstanbul/ TÜRKİYE

**EKOTEKS**

**TEST REPORT**  
*DENEY RAPORU*

20013794-  
ing

05-20

**Customer name:** İDEA MODA KONFEKSİYON SAN. VE TİC. LTD. ŞTİ  
**Address:** SIRACEVİZLER CAD. GÜVENÇ SOK. NO:3 BOMONTI İŞ MERKEZİ  
KAT:2 DAİRE:18/23 ŞİŞLİ/İSTANBUL  
**Buyer name:**  
**Contact Person:**  
**Order No:** -  
**Article No:** -  
**Name and identity of test item:** White mask.  
**The date of receipt of test item:** 29.04.2020  
**Re-submitted/re-confirmation date:** -  
**Date of test:** 29.04.2020-08.05.2020  
**Remarks:** -  
**Sampling:** The results given in this report belong to the received sample by vendor.  
**End-Use:** -  
**Care Label:** Not specified.  
**Number of pages of the report:** 4

**Seal**

**Date**  
08.05.2020

**Customer Representative**  
Servin YURTSEVEN

**Head of Testing Laboratory**  
Sevim A. RAZAK  
08.05.2020

This report shall not be reproduced other than in full except with the permission of the laboratory.  
*Testing reports without signature and seal are not valid.*

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

20013794-  
ing

05-20

REQUIRED TESTS	RESULT	COMMENTS
<b>MICROBIOLOGICAL TESTS</b>		
Bacterial Filtration Efficiency-BFE <sup>(1)</sup>	P	Type I
Microbial Cleanliness(Bioburden) <sup>(2)</sup>	P	
<b>PHYSICAL PROPERTIES</b>		
Breathability(Differential Pressure) <sup>(3)</sup>	P	
P: Pass F: Fail R: Refer to retailer technologist. <sup>(1)</sup> Test results were evaluated according to EN 14683:2019+AC:2019 Annex-B/Table- 1)limit values <sup>(2)</sup> Test results were evaluated according to EN ISO 11737-1:2018 limit values <sup>(3)</sup> Test results were evaluated according to EN 14683:2019+AC:2019 Annex -C/Table- 1 limit values		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified.If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95 %. Tests marked (\*) in this report are not included in the accreditation schedule.



Gen.f136-2/03

This report shall not be reproduced other than in full except with the permission of the laboratory.  
*Testing reports without signature and seal are not valid.*

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

20013794-  
ing

05-20

## TEST RESULTS

### BACTERIAL FILTRATION EFFICIENCY (BFE)

Test Metod: EKOTEKS 70 (In-House Method-Bacterial Filtration Efficiency Testing –BFE /Ref: EN 14683:2019+AC:2019 Medical Face Masks,Requirements and Test Methods (\*)

A specimen of the mask material is clamped between a impactor and an aerosol chamber. An aerosol of *Staphylococcus aureus* is introduced into the aerosol chamber and drawn through the mask material and the impactor under vacuum. The bacterial filtration efficiency of the mask is given by the number of colony forming units passing through the medical face mask material expressed as a percentage of the number of colony forming units present in the challenge aerosol.

<b>Test Flow Rate</b>	28,3 L/min
<b>Test Flow Time</b>	2 minute
<b>Sample Sizes</b>	5 pieces mask
<b>Microorganism</b>	<i>Staphylococcus aureus</i> ATCC 6538
<b>Bacterial concentration (cfu/ ml )</b>	5x10 <sup>5</sup> cfu/ ml
<b>incubation conditions</b>	24 hour, 35°C ± 2°C
<b>Positive control sample average of number of Bacteria (C)</b>	1.7x10 <sup>3</sup> cfu/ ml

RESULTS			
Number of Test Sample	Test Sample (T) Number of Bacteria (cfu/ml)	Bacterial Filtration Efficiency ( % B )	Requirement BFE (%)
1	65	%96.8	Type I ≥95  Type II ≥98
2	63	%96.9	
3	60	%97.0	
4	60	%97.0	
5	57	%97.2	

cfu: Colony-forming unit

$$B = ( C - T ) / C \times 100$$

%B: Bacterial Filtration Efficiency

C: is the mean of the total plate counts for the two positive control runs

T: is the total plate count for the test specimen

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

20013794-  
ing

05-20

## TEST RESULTS

### MICROBIAL CLEANLINESS (Bioburden)

**Test Metod:** Ref: EN ISO 11737-1:2018 (\*)

The sample is put in extraciton liquid after shaking well, inoculated on the agar.  
After incubation at  $30 \pm 1$  ° C for 72 hours, growth microorganisms are counted on the agar.

	<b><u>RESULTS</u></b>	<b><u>REQUIREMENT</u></b>
<b>Microbial cleanliness (cfu/g)</b>	24 kob/g	$\leq 30$ cfu/g Type I and Type II mask

### BREATHABILITY (Differential Pressure)

**Test Method :** EKOTEKS 70 - Ref: EN 14683:2019+AC:2019 EK-C (\*)

Test area is 25 mm in diameter , 5 different sample was taken  
Adjusted airflow is 8 l/min.The differential pressure is read directly using a differential pressure manometer .

	<b><u>RESULT</u></b>	<b><u>REQUIREMENT</u></b>
<b>Differential Pressure) (Pa/cm<sup>2</sup>)</b>	30.1 Pa/cm <sup>2</sup> (*)	$< 40$ Pa/cm <sup>2</sup> Type I and Type II mask

\*average results are given